


06 >




GOLF


GOLF

140 GREEN



Golf artificial grass with exceptional durability and performance, featuring a bicolor green design for a realistic, professional surface ideal for putting greens.


 Product characteristics	Unit of measure	Data	Tolerance
Pile height	mm	12	+/- 5 %
Yarn length	mm	32	+/- 5 %
Gauge		3/16	
Stitch rate for sqm	nr	75.000	+/- 10 %
Filaments for sqm	nr	1.200.000	+/- 10 %
Needles for sdm		21,00	
Water permeability	l/h for sqm	1000 L/H	
Total weight	gr/sqm	3.253	+/- 10 %
Roll width	m	4,08	+/-1,00%
Rolls length	m	upon request	+/-1,00%
 Yarn characteristics	Unit of measure	Data	Tolerance
Yarn count	dtex	8.640	+/- 6 %
Thickness	micron	175	+/- 6 %
Composition		100% Polyethylene	
Yarn shape		Monofilo testurizzato	
Color		Bicolour (light and dark green)	
Total yarn weight	gr/sqm	2.080	+/- 5 %
 Backing characteristics	Unit of measure	Data	Tolerance
Primary backing composition (first and second layer)		Polypropylene/Poly-ester	
Primary backing weight	gr/sqm	223	+/- 6 %
Coating		LATEX	
Weight of coating	gr/sqm	950	+/- 6 %






Infill recommendations	Unit of measure	Data	Tolerance
Silica sand			
Granulometry	mm	0.2-0.4	+/- 10 %
Apparent density	gr/cm3	1,50	+/- 15 %
Friability	%	20,00	
Water permeability	cm/h	>50	
Quantity	kg/sqm	13	+/- 5 %



440 TEE



Engineered for golf, this artificial grass features a bicolor green design for a realistic tee-off experience, offering superior performance and longevity.

 Product characteristics	Unit of measure	Data	Tolerance
Pile height	mm	42	+/- 5 %
Yarn length	mm	92	+/- 5 %
Gauge		3/8	
Stitch rate for sqm	nr	20.000	+/- 10 %
Filaments for sqm	nr	240.000	+/- 10 %
Needles for sdm		10,50	
Water permeability	l/h for sqm	1000 L/H	
Total weight	gr/sqm	3.663	+/- 10 %
Roll width	m	4,04	+/-1,00%
Rolls length	m	upon request	+/-1,00%
 Yarn characteristics	Unit of measure	Data	Tolerance
Yarn count	dtex	13.500	+/- 6 %
Thickness	micron	345	+/- 6 %
Composition		100% Polyethylene	
Yarn shape		Monofilament sect.S	
Color		Bicolour (light and dark green)	
Total yarn weight	gr/sqm	2.490	+/- 5 %
 Backing characteristics	Unit of measure	Data	Tolerance
Primary backing composition (first and second layer)		100% Polypropylene	
Primary backing weight	gr/sqm	223	+/- 6 %
Coating		LATEX	
Weight of coating	gr/sqm	950	+/- 6 %



Infill recommendations	Unit of measure	Data	Tolerance
Silica sand			
Granulometry	mm	0.2-0.4	+/- 10 %
Apparent density	gr/cm3	1,50	+/- 15 %
Friability	%	20,00	
Water permeability	cm/h	>50	
Quantity	kg/sqm	16	+/- 5 %

